

Paramastic

1/1

DESCRIPTION

PARAMASTIC is an one-pack polybuteen sealant with outstanding weathering properties. It forms a skin but does not harden.

APPLICATION

PARAMASTIC can be used for sealing of connecting joints in the building industry, around doors and frames, etc.

PARAMASTIC can be used for all joints with poor elongation (max 7.8 %). Has a good adhesion on most undergrounds. Does not stain on porous materials. Is paintable with paint based on solvent.

PROCESSING TEMPERATURE

Between +1 °C and +35 °C.

SURFACES

All surfaces should be dry, clean and free from dust or grease. When necessary, degrease with **Top Cleaner**, MEK, alcohol or ethanol. If necessary, use a primer. It is recommended that adhesion tests are carried out to determine the suitability of the product for its application.

TOOLING

When needed with **DL100** or tools.

CLEANING

With white-spirit or toluene

COLOURS

cream, grey

LIMITATIONS

Max. Joint dimensions 10x10 mm.

SHELF LIFE

Min. 6 months if kept in the original packing and stored in cool and dry conditions between +5 °C and +25 °C.

PACKING

Cartridges of 310 ml, 25 per box

SAFETY

Keep out of reach of children. Please wear protective clothing. Work under local exhaust/ventilation. Keep container tightly closed. Keep away from ignition sources/sparks.

When contact with eyes: rinse immediately with plenty of water for 15 minutes. When contact with skin: wash immediately with lots of water (15 minutes), soap may be used. Consult our safety data sheet.

TECHNICAL CHARACTERISTICS

Type of sealant	Polybutene
Vulcanisation rate (23 °C en 50% R.V.)	Skins within 24 hours but does not vulcanise
Density (ISO 1183)	1,63 g/ml
Temperature resistance	-20 °C - + 80 °C

032013

The data on this sheet have been drafted according to the last state of the laboratory data. Technical characteristics can be changed or adapted. We are not responsible in case of incompleteness. Before usage, one needs to ensure that the product is suitable for its application. Therefore, tests are necessary. Our general conditions apply.