



CHARACTERISTICS

- Neutral alcoxy curing, 1-component silicone sealant (RTV-1)
- Replaces the traditional window mastic
- Sealant compound with permanent elasticity
- Very easy to apply and to maintain
- No wrinkles or cracks

APPLICATIONS

- Is used in renovation projects for window restoration.
- Is applied as a joint in triangular form, as windows used to be installed.
- Is used when installing insulating glass, laminated glass and restoration glass in wooden or steel frames with or without division.
- Appropriate for joints with ample movement.

TECHNICAL CHARACTERISTICS	
Viscosity	Pasty
Vulcanising system	Through moisture in the air
Skin forming	14 min
Curing	1 day: 3 mm 4 days: 6 mm
Density : ISO 1183	1,3 g/ml
Processing temperature	+5°C - +30°C
Shelf life, in the original packing in dry conditions between +5°C - +25°C	9 months
Shore A hardness : DIN 53505/ISO 868	41
Deformation capability : ISO 11600	7,5%
Modulus at break : ISO 8339	0,6 N/mm ²
% Elongation at break : ISO 8339	>100%
Shrinkage	<3%
Temperature resistance	-40°C - +120°C

PACKING AND COLOURS
25 cartridges of 310 ml/box - 48 boxes/pallet
White, black
20 sausages of 600 ml/box - 45 boxes/pallet
White, natural stone, black

Other colours are available on request (75 cartridges or multiples).

METHOD OF USE

Preparation

Parasilico Monument adheres to clean glass, treated wood, metals and plastics. Verify if the lamination was done in accordance with the valid standards and if the surface is free of moist, dust and chips. Degrease the surface with **Parasilico Cleaner** and a clean cloth. Leave the detergent to evaporate. Do not touch the degreased parts. Do not apply in humid weather conditions (rain or mist). (In case of an unidentified surface, please execute prior tests or contact our technical service.) Use fitting **synthetic supports**. Do not use neoprene packers, they might migrate. If the windows are loaded immediately after installation, they should be kept in place mechanically until the sealant compound is completely cured. To support the windows properly, a **PE strip** or **double-faced adhesive tape** must be put into the frame. In case of traditional sealing, ventilated glass is impossible. Therefore all joints must be sealed without air locks.

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply.

Application

Cut off the nozzle diagonally in accordance with the width of the joint, screw on the tube. Apply the sealant compound using a manual or pneumatic gun.

Tooling

Before skin forming, you need to smooth the joint in a triangular shape with a **scraper** and by means of the smoothing agent **DL100**.

Cleaning

Remove stains and clean equipment with **Parasilico Cleaner**. Remove cured sealant compound mechanically using **Silicone Remover**.

SAFETY



The safety data sheet can be obtained upon request.

COMPATIBILITY

Parasilico Monument is compatible with the butyl strip. Thus it can be used for insulating glass. In case the insulating glass is unidentified, please contact our technical service or your window supplier.

TECHNICAL APPROVALS

CE

	
14 DL Chemicals	* Information sur le niveau d'émission de substances volatiles dans l'air intérieur, présentant un risque de toxicité par inhalation, sur une échelle de classe allant de A+ (très faibles émissions) à C (fortes émissions).
EN 15651-2 G No. DoP: MP0030027	

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply.