

Detaprimer 435.10

1/1

DESCRIPTION

DETAPRIMER 435.10 is used for promoting adhesion on non porous materials, certain plastics, paints and ceramics. For porous materials, Primer DL 783 is recommended.

APPLICATION

Undercoat for silicone sealants.

METHOD OF USE

The primer should be applied on the surface with a paintbrush. The sealant has to be applied within 16 hours. For very porous substrates a second layer of primer is necessary

APPLICATION TEMPERATURE

Room temperature

CONSUMPTION

< 80 g/m²

CLEANING TOOLS

nitro-thinner, M.E.C.

PACKING

aluminium bottles of 250 ml and 1000 ml

PRECAUTIONS

Inhaling of the vapours in high concentrations is noxious for the health.

SHELF-LIFE

9 months if kept in the original packing at room temperature

PROPERTIES

Base	mixture of silicone and resins with reactivating addition
Colour	colourless, transparent
Density	0.86 g/cm ³
Viscosity	liquid
Drying time	15 min.
Flash point	< 21°C

072003

The data on this sheet have been drafted according to the last state of the laboratory data. Technical characteristics can be changed or adapted. We are not responsible in case of incompleteness. Before usage, one needs to ensure that the product is suitable for its application. Therefore, tests are necessary. Our general conditions apply.