

Primer DI 783

1/1

DESCRIPTION

PRIMER DL 783 is a one-component colourless synthetic resin-based primer, an acrylate silicon copolymer dissolved in toluene. It is used for porous, highly absorbent surfaces, including alkaline ones. Another advantage of this primer is that primed surfaces can be subjected to permanently wet conditions without any risk of the resin film emulsifying.

PRECAUTIONS

Contains flammable solvents. Vapours should not be inhaled in high concentrations and over long periods.

Keep away from sources of ignition. No smoking. Do not empty into drains. Take precautionary measures against static discharges.

SHELF-LIFE

At least 6 months if kept in closed packing below 25°C

PROPERTIES

Drying time at room temperature	ca. 1 hour
Solids content	ca. 38 %
Specific gravity	0,95 g/cm ³
Colour	colourless
Flash point	+ 8 °C (DIN 51755)
Ignition temperature	+ 500 °C (DIN 51794)

042002

The data on this sheet have been drafted according to the last state of the laboratory data. Technical characteristics can be changed or adapted. We are not responsible in case of incompleteness. Before usage, one needs to ensure that the product is suitable for its application. Therefore, tests are necessary. Our general conditions apply.